

Technical Data Sheet - 2019

Creative Labels

 arjowiggins

Creative Labels

Wove

	Test method	80g	
Extra White			
Caliper (μm)	ISO 534	92	
Bulk ($\mu\text{/gsm}$)	ISO 534	1,2	
Opacity (%)	ISO 2471	87	
Tear resistance MD (N/15mm)	ISO 1924/1	90	
Tear resistance CD (N/15mm)		50	
Stiffness (mN)	M direction	ISO 2493	6
Stiffness (mN)	C direction		3
Ivory			
Caliper (μm)	ISO 534	92	
Bulk ($\mu\text{/gsm}$)	ISO 534	1,2	
Opacity (%)	ISO 2471	90	
Tear resistance MD (N/15mm)	ISO 1924/1	90	
Tear resistance CD (N/15mm)		50	
Stiffness (mN)	M direction	ISO 2493	6
Stiffness (mN)	C direction		3
Extra White 100% Recycled			
Caliper (μm)	ISO 534	100	
Bulk ($\mu\text{/gsm}$)	ISO 534	1,25	
Opacity (%)	ISO 2471	90	
Tear resistance MD (N/15mm)	ISO 1924/1	70	
Tear resistance CD (N/15mm)		40	
Stiffness (mN)	M direction	ISO 2493	8
Stiffness (mN)	C direction		5



Creative Labels

Wove Metallics

		Test method	85g
Cryogen White			
Caliper (µm)		ISO 534	110
Bulk (µ/gsm)		ISO 534	1,2
Whitest shade opacity (%)		ISO 2471	89
Tear resistance MD (N/15mm)		ISO 1924/1	90
Tear resistance CD (N/15mm)			50
Stiffness (mN)	M direction	ISO 2493	10
Stiffness (mN)	C direction		5
Ice Silver, Lustre			
Caliper (µm)		ISO 534	110
Bulk (µ/gsm)		ISO 534	1,3
Whitest shade opacity (%)		ISO 2471	90
Tear resistance MD (N/15mm)		ISO 1924/1	90
Tear resistance CD (N/15mm)			50
Stiffness (mN)	M direction	ISO 2493	14
Stiffness (mN)	C direction		7



Creative Labels

Rough Laid

		Test method	80g
Natural White, Ivory			
Caliper (μm)		ISO 534	110
Bulk ($\mu\text{/gsm}$)		ISO 534	1,35
Whitest shade opacity (%)		ISO 2471	90
Tear resistance MD (N/15mm)		ISO 1924/1	80
Tear resistance CD (N/15mm)			50
Stiffness (mN)	M direction	ISO 2493	11
Stiffness (mN)	C direction		6
Extra White			
Caliper (μm)		ISO 534	110
Bulk ($\mu\text{/gsm}$)		ISO 534	1,3
Whitest shade opacity (%)		ISO 2471	90
Tear resistance MD (N/15mm)		ISO 1924/1	80
Tear resistance CD (N/15mm)			50
Stiffness (mN)	M direction	ISO 2493	11
Stiffness (mN)	C direction		6
Cream			
Caliper (μm)		ISO 534	110
Bulk ($\mu\text{/gsm}$)		ISO 534	1,35
Whitest shade opacity (%)		ISO 2471	90
Tear resistance MD (N/15mm)		ISO 1924/1	80
Tear resistance CD (N/15mm)			50
Stiffness (mN)	M direction	ISO 2493	11
Stiffness (mN)	C direction		6



Creative Labels

Martelé

		Test method	85g
Extra White			
Caliper (μm)		ISO 534	110
Bulk ($\mu\text{/gsm}$)		ISO 534	1,3
Whitest shade opacity (%)		ISO 2471	90
Tear resistance MD (N/15mm)		ISO 1924/1	70
Tear resistance CD (N/15mm)			50
Stiffness (mN)	M direction	ISO 2493	10
Stiffness (mN)	C direction		6
Ivory			
Caliper (μm)		ISO 534	120
Bulk ($\mu\text{/gsm}$)		ISO 534	1,4
Whitest shade opacity (%)		ISO 2471	90
Tear resistance MD (N/15mm)		ISO 1924/1	90
Tear resistance CD (N/15mm)			60
Stiffness (mN)	M direction	ISO 2493	10
Stiffness (mN)	C direction		5



Creative Labels

Linen

		Test method	85g
Extra White			
Caliper (μm)		ISO 534	115
Bulk ($\mu\text{/gsm}$)		ISO 534	1,35
Whitest shade opacity (%)		ISO 2471	90
Tear resistance MD (N/15mm)		ISO 1924/1	70
Tear resistance CD (N/15mm)			60
Stiffness (mN)	M direction	ISO 2493	10
Stiffness (mN)	C direction		6
Ivory			
Caliper (μm)		ISO 534	115
Bulk ($\mu\text{/gsm}$)		ISO 534	1,35
Opacity (%)		ISO 2471	88
Tear resistance MD (N/15mm)		ISO 1924/1	70
Tear resistance CD (N/15mm)			60
Stiffness (mN)	M direction	ISO 2493	10
Stiffness (mN)	C direction		6



Creative Labels

Millésime

		Test method	85g
Extra White			
Caliper (μm)		ISO 534	120
Bulk ($\mu\text{/gsm}$)		ISO 534	1,4
Whitest shade opacity (%)		ISO 2471	88
Bendtsen roughness (ml/min)			
Tear resistance MD (N/15mm)		ISO 1924/1	90
Tear resistance CD (N/15mm)			60
Stiffness (mN)	M direction	ISO 2493	10
Stiffness (mN)	C direction		5
Ivory			
Caliper (μm)		ISO 534	120
Bulk ($\mu\text{/gsm}$)		ISO 534	1,4
Whitest shade opacity (%)		ISO 2471	84
Tear resistance MD (N/15mm)		ISO 1924/1	80
Tear resistance CD (N/15mm)			50
Stiffness (mN)	M direction	ISO 2493	8
Stiffness (mN)	C direction		4



Creative Labels

Shetland

		Test method	85
Extra White			
Caliper (μm)		ISO 534	120
Bulk ($\mu\text{/gsm}$)		ISO 534	1,4
Whitest shade opacity (%)		ISO 2471	87
Tear resistance MD (N/15mm)		ISO 1924/1	90
Tear resistance CD (N/15mm)			60
Stiffness (mN)	M direction	ISO 2493	8
Stiffness (mN)	C direction		4

FSC™ C018501

